INTERNATIONAL JOURNAL OF SCIENTIFIC & EDUCATIONAL RESEARCH
VOLUME I, ISSUE II ISSN: 2475-3238

ADVANCED SYNTHESIS STRATEGIES FOR HIGH-PERFORMANCE ZINC-ION BATTERY

Diyorbek Absattorov
Laboratory Assistant, Department of Metrology and Materials Science Engineering at Karshi State Technical University
Dilnoza Erimbatova
PhD student at Karakalpak State University
Murodjon Samadiy
Professor at Karshi State Technical University

ARTICLE INFO:
Received:11.10.2026
Revised: 12.10.2026
Accepted:13.10.2026
KEY WORDS:
zinc-ion battery; cathode materials; co-precipitation; manganese oxide; vanadium oxide; Prussian blue analogues; energy storage

ABSTRACT

Aqueous zinc-ion batteries are attractive for grid storage because they are safe, cheap and built from abundant materials. Their progress depends mostly on the cathode, which must host zinc ions reversibly in a water-based electrolyte. This article reviews how synthesis choices shape the structure and performance of manganese, vanadium and Prussian blue cathodes, with special attention to co-precipitation. We describe the method step by step, compare it with other routes, and point out what still limits practical use. Controlled reaction conditions, defect management and conductive coatings are the most reliable ways to improve capacity and cycle life.

1. Introduction

Demand for stationary energy storage keeps growing as solar and wind power expand, and lithium-ion batteries are not always the best fit for this job. Their organic electrolytes are flammable, and cost and resource concerns become serious at grid scale. Rechargeable zinc-ion batteries (ZIBs) have therefore drawn strong interest, since zinc metal is stable in water, has a high theoretical capacity and is easy to handle [1]. The electrolyte is usually a mild aqueous salt solution, which makes the cell safer and simpler to assemble than non-aqueous systems [2].

Even so, the technology is far from finished. Unlike Li^+, the Zn^{2+} ion carries two charges and is strongly hydrated, so it interacts heavily with the host lattice and moves slowly through it [1]. Many materials that work well in lithium cells therefore perform poorly with zinc. Early

demonstrations showed that frameworks such as NASICON-type phosphates could host Zn^{2+} reversibly [3], and layered manganese oxides soon followed [4]. Since then, vanadium-based compounds have been studied intensively because their open layers and variable oxidation states allow high capacity [5].

Manganese dioxide has stayed popular for practical reasons: it is inexpensive, nontoxic and available in many crystal forms [4]. Its drawbacks are poor electronic conductivity and partial dissolution during cycling, which is why researchers often combine it with carbon nanotubes or other conductive supports [6]. A third family, the Prussian blue analogues, offers wide ionic channels and good rate behavior, although capacity is moderate [7][8]. The reaction mechanisms in all these materials are still debated, and several processes can occur together [7].

What links these materials is that their final properties depend heavily on how they are made. Particle size, crystallinity, water content, defect density and surface coating are all set during synthesis, and each affects ion diffusion and stability [2][9]. Reports of the same compound can differ widely in capacity simply because the preparation route was different. Composite and freestanding electrodes show the same trend, as the arrangement of active material and conductive framework strongly affects the result [10]. This article therefore focuses on synthesis, and in particular on co-precipitation, which is simple, low-energy and easy to scale. We hope to give newcomers a clear and practical overview.

2. Literature Review

Early work on ZIB cathodes concentrated on finding any structure that could accept zinc. Alfaruqi et al. reported that nanoflakes of layered δ-MnO_2 delivered high zinc-storage capacity, which highlighted the value of a layered structure and a thin morphology [4]. Xu and co-workers prepared MnO_2 combined with acid-treated carbon nanotubes and found that the conductive network improved storage behavior compared with the oxide alone [6].

Vanadium compounds soon became the second major direction. Tang and colleagues showed that potassium vanadates with stable frameworks and fast ion channels could cycle well in aqueous cells, suggesting that pre-inserted cations act as pillars that stop layers from collapsing [5]. Dai et al. later grew VO_2 on graphene to make freestanding films, achieving stable cycling and good rate performance without binders [10].

Prussian blue analogues were studied in parallel. Jia et al. described a copper hexacyanoferrate with an open framework that could serve as a positive electrode in zinc cells [8].

Taken together, these studies point to the same conclusion: composition matters, but the way the material is built matters just as much.

3. Materials and Methods

This is a review article, so no new experimental data are presented. Instead, this section describes the co-precipitation procedure and the evaluation steps most often used in the cited literature.

3.1 Co-precipitation procedure. Co-precipitation means that two or more dissolved species form a solid together when a solution is changed in a controlled way. For zinc-ion cathodes, it is most often used for Prussian blue analogues [8][9]. A transition-metal salt solution (for example Cu^{2+} or Zn^{2+} salts) and a hexacyanoferrate solution are prepared separately in deionized water. They are then added dropwise into a stirred vessel at room temperature or slightly above. A chelating agent such as sodium citrate is often placed in one solution to slow nucleation, so that crystals grow gradually instead of forming at once [9]. When several metals are used, they are dissolved together, which forces them to settle in the same particles and gives an even composition [9].

3.2 Key parameters. Four variables matter most. Addition rate: fast mixing gives many small, defective crystals, while slow mixing gives larger and more ordered ones. Concentration: lower concentrations favor regular growth. Temperature and pH: these control solubilities and the oxidation state of the metals, and are usually held constant during the reaction. Ageing time: leaving the suspension to stand for several hours lets crystals ripen and heal defects [8][9]. Carbon nanotubes or graphene can be dispersed in the solution beforehand so that particles grow directly on the conductive support [6][10].

3.3 Post-treatment. The precipitate is collected by filtration or centrifugation, washed several times with water and ethanol to remove residual salts, and dried under mild heat or vacuum. For oxides and phosphates, the dried precursor is often heated in air to obtain the final crystal phase [3][4]. Drying temperature must be chosen carefully, because removing too much lattice water can damage Prussian blue frameworks.

4. Discussion

Each route involves a trade-off. Co-precipitation needs little energy, simple equipment and gives uniform mixing of elements, so it is the easiest to scale. Its weakness is limited control over particle shape and a tendency to leave vacancies and trapped water, which reduce stability in Prussian blue materials [9]. Hydrothermal methods give excellent morphology, but batch size is limited and the process is energy-intensive [5]. Solid-state methods are cheap but offer little control over particle size [3]. Composite strategies consistently help, yet they add cost and complexity [6][10].

Several challenges remain. Manganese dissolution, structural collapse in vanadium oxides during deep cycling, and the lack of standard testing conditions all make fair comparison difficult [1][2]. Future work should combine scalable synthesis with in situ characterization, so that the link between preparation and performance can be understood rather than found by trial and error.

5. Conclusion

Zinc-ion batteries are promising for safe and low-cost energy storage, and the cathode remains the main bottleneck. This review shows that the synthesis route strongly influences structure, conductivity and stability in manganese, vanadium and Prussian blue materials. Co-

precipitation stands out as a simple, low-energy and scalable method, provided that mixing speed, concentration and ageing are carefully controlled. Defect engineering, chelating agents and conductive coatings are the most dependable ways to improve cycling. Future studies should aim for standardized testing and deeper mechanistic understanding, which will help turn laboratory cathodes into practical battery components.

References

[1] L.E. Blanc, D. Kundu, L.F. Nazar, Scientific challenges for the implementation of Zn-ion batteries, Joule 4 (2020) 771–799. https://doi.org/10.1016/j.joule.2020.03.002

[2] D. Chen, M. Lu, D. Cai, H. Yang, W. Han, Recent advances in energy storage mechanism of aqueous zinc-ion batteries, J. Energy Chem. 54 (2021) 712–726. https://doi.org/10.1016/j.jechem.2020.06.070

[3] G. Li, Z. Yang, Y. Jiang, et al., Towards polyvalent ion batteries: a zinc-ion battery based on NASICON structured $Na_3V_2(PO_4)_3$, Nano Energy 25 (2016) 211–217. https://doi.org/10.1016/j.nanoen.2016.04.051

[4] M.H. Alfaruqi, J. Gim, S. Kim, et al., A layered δ-MnO_2 nanoflake cathode with high zinc-storage capacities for eco-friendly battery applications, Electrochem. Commun. 60 (2015) 121–125. https://doi.org/10.1016/j.elecom.2015.08.019

[5] B. Tang, G. Fang, J. Zhou, et al., Potassium vanadates with stable structure and fast ion diffusion channel as cathode for rechargeable aqueous zinc-ion batteries, Nano Energy 51 (2018) 579–587. https://doi.org/10.1016/j.nanoen.2018.07.014

[6] D. Xu, B. Li, C. Wei, et al., Preparation and characterization of MnO_2/acid-treated CNT nanocomposites for energy storage with zinc ions, Electrochim. Acta 133 (2014) 254–261. https://doi.org/10.1016/j.electacta.2014.04.001

[7] L. Shan, Y. Yang, W. Zhang, et al., Observation of combination displacement/intercalation reaction in aqueous zinc-ion battery, Energy Storage Mater. 18 (2019) 10–14. https://doi.org/10.1016/j.ensm.2018.09.022

[8] Z. Jia, B. Wang, Y. Wang, Copper hexacyanoferrate with a well-defined open framework as a positive electrode for aqueous zinc ion batteries, Mater. Chem. Phys. 149–150 (2015) 601–606. https://doi.org/10.1016/j.matchemphys.2014.11.017

[9] G. Kasiri, J. Glenneberg, A.B. Hashemi, R. Kun, F. La Mantia, Mixed copper-zinc hexacyanoferrate as cathode material for aqueous zinc-ion batteries, Energy Storage Mater. 19 (2019) 360–369. https://doi.org/10.1016/j.ensm.2019.03.019

[10] X. Dai, F. Wan, L. Zhang, H. Zhang, Z. Niu, Freestanding graphene/VO_2 composite films for highly stable aqueous Zn-ion batteries with superior rate performance, Energy Storage Mater. 17 (2019) 143–150. https://doi.org/10.1016/j.ensm.2018.07.024